



Dura-MED SPECIFICATIONS

Roll Size	1.5 m X 15.2 m (60" nominal x 50')
Gauge	2mm
Colors	16
Surface Profile	Paper textured look
ASTM F-1859	Complies Type 1
ASTM E-648/NFPA 253 – Fire Resistance	Class 1
Critical Radiant Flux CRF	>1.10
ASTM E-662 – Smoke Density	Class 1 \leq 450
New York State Fire Prevention Code	Complies with Article 15, Part 1120
New York City Fire Prevention Code	Accepted under section 27-348
ASTM D-3389 Abrasion Resistance (H-18 500 gr @ 1,000 cycles)	0.3g
ASTM D-471 - Oil & Grease Resistance	Excellent
ASTM D-2047 - Static Coefficient of Friction	0.75
ASTM E-2179 - Impact Sound Transmission	16 dB
ASTM E-492 - Airborne Sound	16 dB
ASTM D-2240 - Hardness	\geq 85 Shore A
ASTM F-970 - Static Load (modified)	2,000 PSI
ASTM D-297 - Density	1.72g
ASTM D-412 - Tensile	1,000 PSI
ASTM D-412 - Elongation	170%
ASTM D-624 - Tear Die	190 lb/in
ASTM F-925 - Chemical Resistance	Acids, Alkalis, Solvents – Excellent (Available on request)
VOCs (Volatile Organic Compounds)	Very Low

Estrie Products International, a Division of American Biltrite (Canada) Ltd.

Telephone: 1-800-479-0190

Fax: 1-800-810-5731

E-Mail: flooring@american-biltrite.com



June 24, 2008

Version 003

Page 1 of 2



Dura-MED SPECIFICATIONS

ASTM F-1515 - Light Stability	Complies
ASTM F-1514 - Heat Stability	Complies
ESD S. 7. 1 - Electrical Resistance	$\geq 10^{10}$ ohms
Indoor Air Quality	FloorScore Certified by SCS, Certification No. SCS-FS-01492
Limited Wear Warranty	10 years
ANTIBACTERIAL	
IMPORTANT: All Dura-MED rubber flooring contains naturally occurring inhibitors that resist the growth of bacteria, fungus and mould.	

