



AB-3275 NEOPRENE CLOTH INSERTED PACKING

GRADE	Industrial
FINISH	Smooth
POWDER	Yes
TRIMMED	Yes
COLOR	Black
FABRIC	Polyester

TECHNICAL SPECIFICATIONS

SPECIFICATION ASTM D2000 1BC712

POLYMER: NITRILE, STYRENE-BUTADIENE, NEOPRENE (NBR/SBR/CR)

ASTM	DESCRIPTION	VALUE
	SPECIFIC GRAVITY (gr/cc)	1.42
D2240	HARDNESS (shore A)	70
D412	TENSILE (psi)	1200 min.
	ULTIMATE ELONGATION (%)	250 min.
D395B	COMPRESSION SET	22 hrs @ 100°C (212°F) 80% max.
D573	HEAT AGING	70 hrs @ 100°C (212°F) Changed Hardness: +/-15 points max. Tensile: +/-30% max. Elongation: - 50% max.
D471	OIL AGING #3	70 hrs @ 100°C (212°F) Volume changed: 120% max.
TEMPERATURE RANGE (general guideline)		-20° to 190°F (-29° to 88°C)

Mullen Burst 1 Ply: 600 psi typical

Maximum pieces per roll: 2

Minimum piece length: 5'

Width tolerance: -0 / +1"

Fabric 9 oz. polyester

Material is within commercial sheet rubber gauge tolerances.

Typical values do not constitute a specification.

Please ensure the product meets your application specification prior to order placement.

Specifications are subject to change without notice. The website version prevails.

AB-3275 NEOPRENE CLOTH INSERTED PACKING

	GAUGE IN (MM)	WIDTH IN (MM)	SURFACE/ROLL SFT (M ²)	LENGTH/ROLL LFT (M)	WEIGHT/ROLL LBS (KG)
327-04-602	1/16 (1.60) 1 PLY	60 (1524.0)	250 (23.22)	50 (15.24)	104 (47.2)
327-08-602	1/8 (3.20) 1 PLY	60 (1524.0)	125 (11.61)	25 (7.62)	109 (49.4)
327-12-602 ¹	3/16 (4.80) 2 PLY	60 (1524.0)	100 (9.29)	20 (6.09)	126 (57.2)
327-16-602 ¹	1/4 (6.35) 2 PLY	60 (1524.0)	75 (6.96)	15 (4.57)	129 (58.5)
328-08-602	1/8 (3.20) 2 PLY	60 (1524.0)	125 (11.61)	25 (7.62)	113 (51.3)
328-12-602 ¹	3/16 (4.80) 3 PLY	60 (1524.0)	100 (9.29)	20 (6.09)	135 (61.2)
328-16-602	1/4 (6.35) 4 PLY	60 (1524.0)	75 (6.96)	15 (4.57)	130 (58.9)

¹ Made to order.