



AB-362

GRADE	Commercial
FINISH	Smooth
POWDER	Yes
TRIMMED	Yes
COLOR	Black

TECHNICAL SPECIFICATIONS

SPECIFICATION ASTM D2240 | Z1= HARDNESS 60 +/- 5 SHORE A
 POLYMER: NITRILE (NBR) BLEND

ASTM	DESCRIPTION	VALUE
D2240	HARDNESS (shore A)	60 +/- 5
D412	TENSILE (psi)	800 min.
	ULTIMATE ELONGATION (%)	350 min.
D395B	COMPRESSION SET	22 hrs @ 100°C (212°F) 60% max.
D471	OIL AGING #3	70 hrs @ 100°C (212°F) Volume changed: 120% max.
TEMPERATURE RANGE (general guideline)		-30° to 190°F (-34° to 88°C)

Maximum pieces per roll: 2

Minimum piece length: 10'

Width tolerance: -0 / +1"

Material is within commercial sheet rubber gauge tolerances.

Please ensure the product meets your application specification prior to order placement.
 Specifications are subject to change without notice. The website version prevails.

	GAUGE IN (MM)	WIDTH IN (MM)	SURFACE/ROLL SFT (M ²)	LENGTH/ROLL LFT (M)	WEIGHT/ROLL LBS (KG)
362-04-362	1/16 (1.60)	36 (914.4)	300 (27.87)	100 (30.48)	132 (59.9)
362-04-482	1/16 (1.60)	48 (1219.2)	400 (37.16)	100 (30.48)	196 (88.9)
362-08-362	1/8 (3.20)	36 (914.4)	150 (13.93)	50 (15.24)	147 (66.7)
362-08-482	1/8 (3.20)	48 (1219.2)	200 (18.58)	50 (15.24)	196 (88.9)
362-12-482	3/16 (4.80)	48 (1219.2)	160 (14.86)	40 (12.19)	235 (106.6)
362-16-362	1/4 (6.35)	36 (914.4)	120 (11.15)	40 (12.19)	224 (101.6)
362-16-482	1/4 (6.35)	48 (1219.2)	160 (14.86)	40 (12.19)	298 (133.2)
362-24-482 ¹	3/8 (9.50)	48 (1219.2)	120 (11.15)	30 (9.14)	353 (160.1)
362-32-482 ¹	1/2 (12.70)	48 (1219.2)	120 (11.15)	30 (9.14)	470 (213.2)

¹ Made to order.