



## AB-375

GRADE	Premium
FINISH	Smooth
POWDER	Yes
TRIMMED	Yes
COLOR	Black

### TECHNICAL SPECIFICATIONS

SPECIFICATION ASTM D2000: 2BG725A14B14EA14EF11EF21EO14EO34  
 POLYMER: NITRILE (NBR) (BUNA N)

ASTM	DESCRIPTION	VALUE
	SPECIFIC GRAVITY (gr/cc)	1.18
D2240	HARDNESS (shore A)	70
D412	TENSILE (psi)	2500 min.
	ULTIMATE ELONGATION (%)	300 min.
D395B	COMPRESSION SET	22 hrs @ 100°C (212°F) 25% max.
D573	HEAT AGING	70 hrs @ 100°C (212°F) Changed Hardness: +/-15 points max. Tensile: +/-30% max. Elongation: -50% max.
D471	OIL AGING #3	70 hrs @ 100°C (212°F) Changed Hardness: -10 to +5 points max. Tensile: -45% max. Elongation: -45% max. Volume: 0 to 25% max.
	FLUID RESISTANCE (fuel A)	70 hrs @ 23°C (73.4°F) Changed Hardness: +/-10 points max. Tensile: -25% max. Elongation: -25% max. Volume: -5 to +10% max.
	FLUID RESISTANCE (water)	70 hrs @ 100°C (212°F) Changed Hardness: +/-10 points max. Volume: +/-15% max.
TEMPERATURE RANGE (general guideline)		-20° to 200°F (-30° to 93°C)

**Maximum pieces per roll: 2**

**Minimum piece length: 10'**

**Width tolerance: -0 / +1"**

**Material is within commercial sheet rubber gauge tolerances.**

Please ensure the product meets your application specification prior to order placement.  
 Specifications are subject to change without notice. The website version prevails.

# AB-375

	GAUGE IN (MM)	WIDTH IN (MM)	SURFACE/ROLL SFT (M <sup>2</sup> )	LENGTH/ROLL LFT (M)	WEIGHT/ROLL LBS (KG)
304-02-362 <sup>1</sup>	1/32 (0.80)	36 (914.4)	600 (56.74)	200 (60.96)	118 (53.5)
304-04-362 <sup>1</sup>	1/16 (1.60)	36 (914.4)	300 (27.87)	100 (30.48)	114 (51.7)
304-04-482 <sup>1</sup>	1/16 (1.60)	48 (1219.2)	400 (37.16)	100 (30.48)	157 (71.2)
304-06-482	3/32 (2.38)	48 (1219.2)	300 (27.87)	75 (22.85)	171 (77.6)
304-08-362	1/8 (3.20)	36 (914.4)	150 (13.93)	50 (15.24)	115 (52.2)
304-08-482 <sup>1</sup>	1/8 (3.20)	48 (1219.2)	200 (18.58)	50 (15.24)	153 (69.4)
304-12-362 <sup>1</sup>	3/16 (4.80)	36 (914.4)	120 (11.15)	40 (12.19)	138 (62.6)
304-12-482 <sup>1</sup>	3/16 (4.80)	48 (1219.2)	160 (14.86)	40 (12.19)	185 (83.9)
304-16-362	1/4 (6.35)	36 (914.4)	120 (11.15)	40 (12.19)	174 (78.8)
304-16-482	1/4 (6.35)	48 (1219.2)	160 (14.86)	40 (12.19)	246 (111.6)
304-24-362 <sup>1</sup>	3/8 (9.50)	36 (914.4)	90 (8.36)	30 (9.14)	207 (93.9)
304-24-482 <sup>1</sup>	3/8 (9.50)	48 (1219.2)	120 (11.15)	30 (9.14)	276 (125.2)
304-32-362 <sup>1</sup>	1/2 (12.70)	36 (914.4)	90 (8.36)	30 (9.14)	276 (125.2)
304-32-482 <sup>1</sup>	1/2 (12.70)	48 (1219.2)	120 (11.15)	30 (9.14)	368 (166.9)

<sup>1</sup> Made to order.