



**AB-263**

GRADE	Premium
FINISH	Smooth
POWDER	Yes
TRIMMED	Yes
COLOR	Black

**TECHNICAL SPECIFICATIONS**

**SPECIFICATION ASTM D2000: 3BC609A14C12EO34**  
**POLYMER: NEOPRENE, STYRENE-BUTADIENE, NITRILE (CR/SBR/NBR)**

ASTM	DESCRIPTION	VALUE
	SPECIFIC GRAVITY (gr/cc)	1.37
D2240	HARDNESS (shore A)	60
D412	TENSILE (psi)	900 min.
	ULTIMATE ELONGATION (%)	300 min.
D1149	OZONE RESISTANCE	70 hrs @ 50 PPHM @ 40°C/°F No cracking
D395B	COMPRESSION SET	22 hrs @ 100 °C (212°F) 80% max.
D573	HEAT AGING	70 hrs @ 100°C (212°F) Changed Hardness: +/-15 points max. Tensile: -15% max. Elongation: -40% max.
D471	OIL AGING #3	70 hrs @ 100°C (212°F) Changed Tensile: -60% max. Elongation: -50% max. Volume: 100% max.
TEMPERATURE RANGE (general guideline)		-20° to 190°F (-29° to 88°C)

**Maximum pieces per roll: 1/32" = 3 pieces, 1/16" to 1/2" = 2 pieces, 5/8" to 1" = 1 piece**  
**Minimum piece length: 10'**  
**Width tolerance: -0 / +1"**  
**Meets FMVSS302 "Specimens did not ignite or were self-extinguishing"**  
**ASTM C1166, Flame Propagation with average flame propagation of 39 mm and did not drip flames**  
**Material is within commercial sheet rubber gauge tolerances.**  
**Contains 55% Neoprene polymer base.**

Please ensure the product meets your application specification prior to order placement.  
 Specifications are subject to change without notice. The website version prevails.

# AB-263

	GAUGE IN (MM)	WIDTH IN (MM)	SURFACE/ROLL SFT (M <sup>2</sup> )	LENGTH/ROLL LFT (M)	WEIGHT/ROLL LBS (KG)
264-02-362 <sup>1</sup>	1/32 (0.80)	36 (914.4)	600 (56.74)	200 (60.96)	128 (58.1)
264-02-482	1/32 (0.80)	48 (1219.2)	800 (74.32)	200 (60.96)	170 (77.1)
264-04-362 <sup>1</sup>	1/16 (1.60)	36 (914.4)	300 (27.87)	100 (30.48)	130 (58.9)
264-04-482	1/16 (1.60)	48 (1219.2)	400 (37.16)	100 (30.48)	173 (78.4)
264-06-362 <sup>1</sup>	3/32 (2.38)	36 (914.4)	225 (20.90)	75 (22.85)	149 (67.6)
264-06-482	3/32 (2.38)	48 (1219.2)	300 (27.87)	75 (22.85)	198 (89.8)
264-08-362	1/8 (3.20)	36 (914.4)	150 (13.93)	50 (15.24)	131 (59.4)
264-08-482	1/8 (3.20)	48 (1219.2)	200 (18.58)	50 (15.24)	173 (78.5)
264-08-602	1/8 (3.20)	60 (1524.0)	250 (23.22)	50 (15.24)	217 (98.4)
264-12-362 <sup>1</sup>	3/16 (4.80)	36 (914.4)	120 (11.15)	40 (12.19)	164 (74.4)
264-12-482	3/16 (4.80)	48 (1219.2)	160 (14.86)	40 (12.19)	219 (99.3)
264-12-602	3/16 (4.80)	60 (1524.0)	200 (18.58)	40 (12.19)	256 (116.1)
264-16-362	1/4 (6.35)	36 (914.4)	120 (11.15)	40 (12.19)	219 (99.3)
264-16-482	1/4 (6.35)	48 (1219.2)	160 (14.86)	40 (12.19)	291 (132.0)
264-16-602	1/4 (6.35)	60 (1524.0)	175 (16.25)	35 (10.66)	303 (137.4)
264-24-362	3/8 (9.50)	36 (914.4)	90 (8.36)	30 (9.14)	244 (110.7)
264-24-482	3/8 (9.50)	48 (1219.2)	120 (11.15)	30 (9.14)	324 (146.9)
264-32-362 <sup>1</sup>	1/2 (12.70)	36 (914.4)	90 (8.36)	30 (9.14)	328 (148.8)
264-32-482	1/2 (12.70)	48 (1219.2)	120 (11.15)	30 (9.14)	436 (197.8)
264-40-482 <sup>1</sup>	5/8 (15.90)	48 (1219.2)	120 (11.15)	30 (9.14)	483 (219.1)
264-48-362	3/4 (19.00)	36 (914.4)	90 (8.36)	30 (9.14)	482 (218.6)
264-48-482 <sup>1</sup>	3/4 (19.00)	48 (1219.2)	120 (11.15)	30 (9.14)	642 (291.2)
264-64-362 <sup>1</sup>	1 (25.40)	36 (914.4)	90 (8.36)	30 (9.14)	564 (255.8)
264-64-482	1 (25.40)	48 (1219.2)	100 (9.29)	25 (7.62)	722 (327.5)

<sup>1</sup> Made to order.