



AB-131

GRADE	Industrial
FINISH	Smooth
POWDER	Yes
TRIMMED	Yes
COLOR	Red

TECHNICAL SPECIFICATIONS

SPECIFICATION ASTM D2000: 2AA325A13F17Z1 | Z1 = HARDNESS 35 +/- SHORE A
POLYMER: NATURAL RUBBER (NR)

ASTM	DESCRIPTION	VALUE
	SPECIFIC GRAVITY (gr/cc)	1.00
D2240	HARDNESS (shore A)	35
D412	TENSILE (psi)	2500 min.
	ULTIMATE ELONGATION (%)	500 min.
D2137	COLD TEMPERATURE	-40°C/°F min.
D395B	COMPRESSION SET	22 hrs @ 70°C (158°F) 50% max.
D573	HEAT AGING	70 hrs @ 70°C (158°F) Changed Hardness: +/-15 points max. Tensile: +/-30% max. Elongation: -50% max.
TEMPERATURE RANGE (general guideline)		-20° to 180°F (-29° to 82°C)

Minimum piece length: 10'

Width tolerance: -0 / +1"

Material is within commercial sheet rubber gauge tolerances.

Please ensure the product meets your application specification prior to order placement. Specifications are subject to change without notice. The website version prevails.

	GAUGE IN (MM)	WIDTH IN (MM)	SURFACE/ROLL SFT (M ²)	LENGTH/ROLL LFT (M)	WEIGHT/ROLL LBS (KG)
135-08-482	1/8 (3.20)	48 (1219.2)	320 (29.73)	80 (24.38)	213 (96.6)
135-12-482	3/16 (4.80)	48 (1219.2)	240 (22.29)	60 (18.29)	228 (103.4)
135-16-482	1/4 (6.35)	48 (1219.2)	160 (14.86)	40 (12.19)	203 (92.1)
135-24-482	3/8 (9.50)	48 (1219.2)	120 (11.15)	30 (9.14)	226 (102.5)