



AB-465

GRADE	Industrial
FINISH	Smooth
POWDER	Yes
TRIMMED	Yes
COLOR	Black

TECHNICAL SPECIFICATIONS

SPECIFICATION ASTM D2000: 3BA610A14C12
POLYMER: BUTYL (IIR)

ASTM	DESCRIPTION	VALUE
	SPECIFIC GRAVITY (gr/cc)	1.24
D2240	HARDNESS (shore A)	60
D412	TENSILE (psi)	1000 min.
	ULTIMATE ELONGATION (%)	300 min.
D1149	OZONE RESISTANCE	70 hrs 50 PPHM @ 40°C/°F No cracking
D395B	COMPRESSION SET	22 hrs @ 70°C (158°F) 50% max.
D573	HEAT AGING	70 hrs @ 100°C (212°F) Changed Hardness: +10 points max. Tensile: -25% max. Elongation: -25% max.
TEMPERATURE RANGE (general guideline)		-30° to 212°F (-34° to 100°C)

Maximum pieces per roll: 2

Minimum piece length: 10'

Width tolerance: -0 / +1"

Material is within commercial sheet rubber gauge tolerances.

Please ensure the product meets your application specification prior to order placement. Specifications are subject to change without notice. The website version prevails.

	GAUGE IN (MM)	WIDTH IN (MM)	SURFACE/ROLL SFT (M ²)	LENGTH/ROLL LFT (M)	WEIGHT/ROLL LBS (KG)
360-04-482 ¹	1/16 (1.60)	48 (1219.2)	400 (37.16)	100 (30.48)	158 (71.7)
360-08-362	1/8 (3.20)	36 (914.4)	150 (13.93)	50 (15.24)	119 (54.0)
360-08-482	1/8 (3.20)	48 (1219.2)	200 (18.58)	50 (15.24)	159 (72.1)
360-12-362 ¹	3/16 (4.80)	36 (914.4)	120 (11.15)	40 (12.19)	144 (65.3)
360-16-362 ¹	1/4 (6.35)	36 (914.4)	120 (11.15)	40 (12.19)	191 (86.6)
360-16-482 ¹	1/4 (6.35)	48 (1219.2)	160 (14.86)	40 (12.19)	255 (115.7)

¹ Made to order.