



STYRENE-BUTADIENE

AB-613

GRADE	Premium
FINISH	Smooth
POWDER	Yes
TRIMMED	Yes
COLOR	Red

TECHNICAL SPECIFICATIONS

**SPECIFICATION ASTM D1330-85 GRADE 1 AND 2
POLYMER: STYRENE-BUTADIENE (SBR)**

ASTM	DESCRIPTION	VALUE
	SPECIFIC GRAVITY (gr/cc)	1.65
D2240	HARDNESS (shore A)	70-85
D412	TENSILE (psi)	700 min.
	ULTIMATE ELONGATION (%)	150 min.
D395 (Method B)	COMPRESSION SET 22 hrs @ 70°C (158°F)	40% max
D573	HEAT AGING 94 hrs @ 70°C (158°F)	Tensile (%): -25 max. Elongation (%): -25 max.
TEMPERATURE RANGE (general guideline)		-20° to 200°F (-29° to 93°C)

Maximum pieces per roll: 2

Minimum piece length: 10'

Width tolerance: -0/ +1"

Durometer tolerance: +5 / -10 max.

Material is within commercial sheet rubber gauge tolerances.

The documentation for sheet rubber gauge tolerances is published on our website. Please ensure the product meets your application specification prior to order placement. Specifications are subject to change without notice. The website version prevails.

	GAUGE IN (MM)	WIDTH IN (MM)	SURFACE/ROLL SFT (M ²)	LENGTH/ROLL LFT (M)	WEIGHT/ROLL LBS (KG)
109-04-362 ¹	1/16 (1.60)	36 (914.4)	300 (27.87)	100 (30.48)	160 (72.6)
109-04-482 ¹	1/16 (1.60)	48 (1219.2)	400 (37.16)	100 (30.48)	219 (99.3)
109-08-362 ¹	1/8 (3.20)	36 (914.4)	195 (18.11)	65 (19.81)	209 (94.8)
109-08-482	1/8 (3.20)	48 (1219.2)	200 (18.58)	50 (15.24)	224 (101.6)
109-12-362 ¹	3/16 (4.80)	36 (914.4)	120 (11.15)	40 (12.19)	194 (88.0)
109-16-362 ¹	1/4 (6.35)	36 (914.4)	120 (11.15)	40 (12.19)	270 (122.5)

¹ Made to order.

