



**DURASHIELD® A+**



GRADE	Premium
FINISH	Smooth
POWDER	No
TRIMMED	Yes
COLOR	Orange

**TECHNICAL SPECIFICATIONS**

SPECIFICATION ASTM D2000: 4AA425A13B13F17  
POLYMER: NATURAL RUBBER (NR/BR)

ASTM	DESCRIPTION	VALUE	
	SPECIFIC GRAVITY (gr/cc)	1.03	
D2240	HARDNESS (shore A)	40	
D412	TENSILE (psi)	2500 min.	3000 typical
	ULTIMATE ELONGATION (%)	500 min.	700 typical
D624	TEAR (lbs/in.)	180 typical	
	DIN ABRASION METHOD 53516	Wet: 12 mm <sup>3</sup> Dry: 120 mm <sup>3</sup>	
D2137	COLD TEMPERATURE	-40°C/°F min.	
D395B	COMPRESSION SET	22 hrs @ 70°C (158°F) 25% max.	
D573	HEAT AGING	70 hrs @ 70°C (158°F) Changed Hardness: +10 points max. Tensile: -25% max. Elongation: -25% max.	
TEMPERATURE RANGE (general guideline)		-40° to 180°F (-40° to 82°C)	

**Maximum pieces per roll: 1**  
**Width tolerance: -0 / +1"**  
**Technical specifications are only for orange DURASHIELD® compound.**  
**Material is within commercial sheet rubber gauge tolerances.**

Typical values do not constitute a specification.  
Please ensure the product meets your application specification prior to order placement.  
Specifications are subject to change without notice. The website version prevails.

# DURASHIELD® A+



	GAUGE IN (MM)	WIDTH IN (MM)	SURFACE/ROLL SFT (M <sup>2</sup> )	LENGTH/ROLL LFT (M)	WEIGHT/ROLL LBS (KG)
153-32-362 <sup>1</sup>	1/2 (12.70)	36 (914.4)	150 (13.93)	50 (15.24)	397 (180.1)
153-32-482 <sup>1</sup>	1/2 (12.70)	48 (1219.2)	200 (18.58)	50 (15.24)	529 (239.9)
153-48-362 <sup>1</sup>	3/4 (19.00)	36 (914.4)	75 (6.96)	25 (7.62)	295 (133.8)
153-48-482 <sup>1</sup>	3/4 (19.00)	48 (1219.2)	100 (9.29)	25 (7.62)	393 (178.3)
153-64-362 <sup>1</sup>	1 (25.40)	36 (914.4)	75 (6.96)	25 (7.62)	397 (180.1)

<sup>1</sup> Made to order.

**This product is also available in slit widths – see SKIRT-SHIELD® A+ on page 10.14.**