



## AB-140 SKIRT-SHIELD® (CUT TO WIDTH)



GRADE	Premium
FINISH	Smooth
POWDER	No
TRIMMED	Yes
COLOR	Red

### TECHNICAL SPECIFICATIONS

SPECIFICATION ASTM D2000: 4AA430A13B13F17  
 POLYMER: NATURAL RUBBER (NR)

ASTM	DESCRIPTION	VALUE	
	SPECIFIC GRAVITY (gr/cc)	1.06	
D2240	HARDNESS (shore A)	40	
D412	TENSILE (psi)	3000min.	3100 typical
	ULTIMATE ELONGATION (%)	600 min.	750 typical
D624	TEAR (lbs/in.)	350 typical	
	DIN ABRASION METHOD 53516	Wet: 40 mm <sup>3</sup> Dry: 160 mm <sup>3</sup>	
D2137	COLD TEMPERATURE	-40°C/°F min.	
D395B	COMPRESSION SET	22 hrs @ 70°C (158°F) 25% max.	
D573	HEAT AGING	70 hrs @ 70°C (158°F) Changed Hardness: +10 points max. Tensile: -25% max. Elongation: -25% max.	
TEMPERATURE RANGE (general guideline)		-40° to 180°F (-40° to 82°C)	

**Material is within commercial sheet rubber gauge tolerances.**

Typical values do not constitute a specification.

Please ensure the product meets your application specification prior to order placement.  
 Specifications are subject to change without notice. The website version prevails.

# AB-140 SKIRT-SHIELD® (CUT TO WIDTH)



	GAUGE IN (MM)	WIDTH IN (MM)	SURFACE/ROLL SFT (M <sup>2</sup> )	LENGTH/ROLL LFT (M)	WEIGHT/ROLL LBS (KG)
132-16-064	1/4 (6.35)	6 (152.4)	---	50 (15.24)	34 (15.4)
132-16-084	1/4 (6.35)	8 (203.2)	---	50 (15.24)	47 (21.3)
132-24-064	3/8 (9.50)	6 (152.4)	---	50 (15.24)	51 (23.1)
132-24-084	3/8 (9.50)	8 (203.2)	---	50 (15.24)	68 (30.8)
132-32-064	1/2 (12.70)	6 (152.4)	---	50 (15.24)	68 (30.8)
132-32-084	1/2 (12.70)	8 (203.2)	---	50 (15.24)	91 (41.3)