



NEOPRENE / POLYCHLOROPRENE

IM-252

GRADE	Commercial
FINISH	Smooth
POWDER	No
TRIMMED	Yes
COLOR	Black

TECHNICAL SPECIFICATIONS

**SPECIFICATION ASTM D2240 | Z1= HARDNESS 50 +/-7 SHORE A
POLYMER: NEOPRENE (CR) BLEND**

ASTM	DESCRIPTION	VALUE
D2240	HARDNESS (shore A)	50 +/-7
D412	TENSILE (psi)	500 typical
	ULTIMATE ELONGATION (%)	300 typical
TEMPERATURE RANGE (general guideline)		-20° to 190°F (-29° to 88°C)

Width tolerance: +/-0.5"

Durometer tolerance: +/-7 points

Material is within commercial sheet rubber gauge tolerances.

Typical values do not constitute a specification.

Please ensure the product meets your application specification prior to order placement.

Specifications are subject to change without notice. The website version prevails.

	GAUGE IN (MM)	WIDTH IN (MM)	SURFACE/ROLL SFT (M ²)	LENGTH/ROLL LFT (M)	WEIGHT/ROLL LBS (KG)
201-04-482	1/16 (1.60)	48 (1219.2)	400 (37.16)	100 (30.48)	198 (89.8)
201-08-482	1/8 (3.20)	48 (1219.2)	200 (18.58)	50 (15.24)	198 (89.8)
201-12-482	3/16 (4.80)	48 (1219.2)	160 (14.86)	40 (12.19)	237 (107.5)
201-16-482	1/4 (6.35)	48 (1219.2)	160 (14.86)	40 (12.19)	316 (143.3)
201-24-482	3/8 (9.50)	48 (1219.2)	120 (11.15)	30 (9.14)	356 (161.5)
201-32-482	1/2 (12.70)	48 (1219.2)	120 (11.15)	30 (9.14)	470 (213.2)