



**AB-139 BLAST®**



GRADE	Industrial
FINISH	Smooth
POWDER	Yes
TRIMMED	Yes
COLOR	Black

**TECHNICAL SPECIFICATIONS**

SPECIFICATION ASTM D2000: 2AA420A13F17  
POLYMER: NATURAL RUBBER (NR)

ASTM	DESCRIPTION	VALUE	
	SPECIFIC GRAVITY (gr/cc)	1.14	
D2240	HARDNESS (shore A)	40	
D412	TENSILE (psi)	2000 min.	2500 typical
	ULTIMATE ELONGATION (%)	400 min.	700 typical
D2137	COLD TEMPERATURE	-40°C/°F min.	
D395B	COMPRESSION SET	22 hrs @ 70°C (158°F) 50% max.	
D573	HEAT AGING	70 hrs @ 70°C (158°F) Changed Hardness: +/-15 points max. Tensile: +/-30% max. Elongation: -50% max.	
TEMPERATURE RANGE (general guideline)		-20° to 180°F (-29° to 82°C)	

Maximum pieces per roll: 2

Minimum piece length: 10'

Width tolerance: -0 / +1"

Material is within commercial sheet rubber gauge tolerances.

Typical values do not constitute a specification.

Please ensure the product meets your application specification prior to order placement.

Specifications are subject to change without notice. The website version prevails.

	GAUGE IN (MM)	WIDTH IN (MM)	SURFACE/ROLL SFT (M <sup>2</sup> )	LENGTH/ROLL LFT (M)	WEIGHT/ROLL LBS (KG)
141-08-482	1/8 (3.20)	48 (1219.2)	160 (14.86)	40 (12.19)	129 (58.5)
141-16-482	1/4 (6.35)	48 (1219.2)	160 (14.86)	40 (12.19)	236 (107.0)
141-24-482 <sup>1</sup>	3/8 (9.50)	48 (1219.2)	120 (11.15)	30 (9.14)	264 (119.7)

<sup>1</sup> Made to order.