



HEAT-GUARD



GRADE	Premium
FINISH	Smooth
POWDER	No
TRIMMED	Yes
COLOR	Black

TECHNICAL SPECIFICATIONS

SPECIFICATION ASTM D2000: 3BA608A14C12F17
 POLYMER: ETHYLENE PROPLYENE DIENE, NEOPRENE TEXTURED BONDING LAYER (EPDM/CR)

ASTM	DESCRIPTION	VALUE
	SPECIFIC GRAVITY (gr/cc)	1.20
D2240	HARDNESS (shore A)	60
D412	TENSILE (psi)	800 min.
	ULTIMATE ELONGATION (%)	300 min.
D395B	COMPRESSION SET	22 hrs @ 70°C (158°F) 50% max.
D573	HEAT AGING	70 hrs @ 100°C (212°F) Changed Hardness: +10 points max. Tensile: -25% max. Elongation: -25% max.
D1149	OZONE RESISTANCE	70 hrs @ 40°C/°F @ 50 ppm No cracks
D2137	COLD TEMPERATURE	-40°C/°F min.
TEMPERATURE RANGE (general guideline)		-40° to 250°F (-40° to 121°C)

Maximum pieces per roll: 2
Minimum piece length: 10'
Width tolerance: -0/ +1"

Technical specifications are for the product without bonding layer.
Material is within commercial sheet rubber gauge tolerances.

Please ensure the product meets your application specification prior to order placement.
 Specifications are subject to change without notice. The website version prevails.

	GAUGE IN (MM)	WIDTH IN (MM)	SURFACE/ROLL SFT (M ²)	LENGTH/ROLL LFT (M)	WEIGHT/ROLL LBS (KG)
322-16-482 ¹	1/4 (6.35)	48 (1219.2)	140 (13.00)	35 (10.67)	219 (99.3)
322-24-482 ¹	3/8 (9.50)	48 (1219.2)	140 (13.00)	35 (10.67)	228 (103.4)
322-32-482 ¹	1/2 (12.70)	48 (1219.2)	140 (13.00)	35 (10.67)	438 (198.7)

¹ Made to order.